

**Last Deck Inc.**  
**VLP-8148.11**

**Crosshatch Adhesion Testing**

<b>Panel #</b>	<b>Dft</b>	<b>Substrate</b>
1	7.0	Aluminum Decking
2	7.5	Aluminum Decking
3	6.9	Aluminum Decking

<b>Dry Crosshatch</b>	<b>24-hr Soak Crosshatch</b>	<b>48-hr Soak Crosshatch</b>	<b>72-hr Soak Crosshatch</b>
5B	5B	5B	5B
5B	5B	5B	5B
5B	5B	5B	5B